

# T-308H

For austenite stainless steel (Medium carbon, 18%Cr-8%Ni STS)

## Classifications

EN ISO 14343-B:2009	: SS 308H	JIS Z 3321:2013	: YS308H
AWS A5.9-2012	: ER308H		

## Description

- TIG welding of 18%Cr-8%Ni austenite stainless steels (AISI STS 304H)
- A various application of the petrochemical , flesh water, medicine and fertilizer industrial apparatuses.

## Typical chemical composition of wire (%)

C	Si	Mn	Ni	Cr
0.05	0.42	2.06	9.80	19.80

## Typical mechanical properties of all-weld metal

	Y.S (MPa)	T.S (MPa)	El. (%)	IV (J)	
				0°C	-196°C
AWS A5.9		min. 550	min. 35		
EN ISO 14343	min. 350	min. 550	min. 30		
Example	362	599	40	210	70